

FABRICS

FEATURES

| NR. | 0101 | 0205 | 0350, 0506, 1111, 1359, 1715 | 0401, 0705, 0907, 1208, 1512 | 0605, 0807, 1450 | 1008, 1618, 1812 |
|-------------------------|---------------------------------|---------------------------------|---------------------------------|---|---------------------------------|---------------------------------|
| COMPOSITION | 65% PES, 35% PES REC | 71% PES, 16% PP, 7% MA, 6% CO | 47% PES, 23% PP, 17% MA, 13% CO | 47% PES REC, 24% PP REC, 10% PES, 10% MA, 9% CO REC | 77% PP, 10% PES, 7% MA, 6% CO | 86% PES, 9% CO, 5% MA |
| WIDTH | 140 | 140 | 140 | 140 | 140 | 140 |
| WEIGHT | 1050 G/LM | 930 G/LM | 620 G/LM | 826 G/LM | 795 G/LM | 756 G/LM |
| ABRASION (MARTINDALE) | 100.000 | 25.000 | 50.000 | 50.000 | 80.000 | 200.000 |
| COLOUR FASTNESS | ISO 4-5 | ISO 4-5 | ISO 4-5 | ISO 4-5 | ISO 4-5 | ISO 4-5 |
| CLEANING | MACHINE WASH 30 DEGREES CELCIUS | MACHINE WASH 30 DEGREES CELCIUS | MACHINE WASH 30 DEGREES CELCIUS | MACHINE WASH 30 DEGREES CELCIUS | MACHINE WASH 30 DEGREES CELCIUS | MACHINE WASH 40 DEGREES CELCIUS |
| CAL 117 | PASS | PASS | PASS | PASS | PASS | PASS |
| BS 5852 - 0 | PASS | PASS | PASS | PASS | PASS | PASS |
| BS 5852 - 1 | UPON REQUEST | PASS | PASS | PASS | PASS | PASS |
| DIN EN ISO 1021 PART I | PASS | PASS | PASS | PASS | PASS | PASS |
| DIN EN ISO 1021 PART II | UPON REQUEST | PASS | PASS | PASS | PASS | PASS |

SAMPLES



PALERMO 0101
PG 6



PALERMO 0205
PG 4



PALERMO 0350
PG 3



PALERMO 0401
PG 4



PALERMO 0506
PG 3



PALERMO 0605
PG 3



PALERMO 0705
PG 4



PALERMO 0807
PG 3



PALERMO 0907
PG 4



PALERMO 1008
PG 4

SAMPLES



PALERMO 1111
PG 3



PALERMO 1208
PG 4



PALERMO 1359
PG 3



PALERMO 1450
PG 3



PALERMO 1512
PG 4



PALERMO 1618
PG 4



PALERMO 1715
PG 3



PALERMO 1812
PG 4